

Roadcraft Safety Products Limited.

Unit 1 Knightcott Industrial Estate • Banwell • Weston Super Mare
• North Somerset • BS29 6JN
Telephone 01934 825850 • Fax 01934 823106

SKID RESISTANCE & RETRO REFLECTIVE PERFORMANCE

Thermoplastic preformed material is supplied to meet standards in respect of skid resistance and retro reflective performance.

We supply with every order a quantity of ground glass granules, giving the option of increasing both skid resistance and retro performance. We recommend all such applications are treated with a covering of granules, as this not only adds value to skid resistance and retro performance, but enhances the appearance of the finished product.

- If initial skid resistance greater than 45 SRV is required, apply ground glass granules immediately after heating the product (typically 250 g/m).
- If initial retro-reflectivity is required, glass beads can be applied to the surface immediately after heating the product (typically 250 g/m glass beads or glass bead/aggregate).